

Polyether bloc amide **PEBAX® MP 1878 SP 01** is a thermoplastic elastomer made of flexible polyether and rigid polyamide. Added to PA6, Pebax® MP1878 enhances the properties of PA6, especially at low temperatures and low humidity content, at the same time maintaining the transparency of the nylon film and improving its soft touch. This SP grade has been developed to be heat and UV resistant.

Main Characteristics	Value	Unit	Test Method
Density	1.09	g/cm ³	ISO 1183
Water Absorption at Equilibrium At 20°C and 50 % RH	1.35	%	ISO 62
Water Absorption At 23°C and 24 h in water	6.7	%	
Melting Point	195	°C	ISO 11357
Vicat Point Under 1 daN	169	°C	ISO 306
Hardness (*) Instantaneous After 15 s	58 54	Shore D Shore D	ISO 868
Flexural Modulus (*)	180	MPa	ISO 178
Tensile Test (*) Stress at Break Strain at Break	60 550	MPa %	ASTM D 638

(*) Samples conditioned 15 days at 23°C - 50 % R.H.

DPT/TDS/US 49902/July 2011

The information contained in this document is based on trials carried out by our Research Centres and data selected from the literature, but shall in no event be held to constitute or imply any warranty, undertaking, express or implied commitment from our part. Our formal specifications define the limit of our commitment. No liability whatsoever can be accepted by Arkema with regard to the handling, processing or use of the product or products concerned which must in all cases be employed in accordance with all relevant laws and/or regulations in force in the country or countries concerned.